

(19)

JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **06192504 A**

(43) Date of publication of application: **12.07.94**

(51) Int. Cl.

**C08L 23/10**

**C08K 3/34**

**C08L 53/00**

(21) Application number: **04342170**

(22) Date of filing: **22.12.92**

(71) Applicant: **MITSUI PETROCHEM IND LTD**

(72) Inventor: **YAMAGUCHI MASAYOSHI  
WAKUMOTO HIROSHI  
ISHIMOTO AKIO**

(54) **POLYPROPYLENE COMPOSITION**

(57) Abstract:

PURPOSE: To obtain a polypropylene composition having excellent rigidity, heat resistance and impact resistance.

CONSTITUTION: A polypropylene composition comprises (A) 65-75 pts.wt. highly crystalline polypropylene having  $\geq 65\%$  crystallinity measured by X-ray diffraction method,  $\geq 0.97$  pendant isotacticity  $1_5$  measured by  $^{13}\text{C}$ -NMR method,  $\geq 6$  molecular weight

distribution obtained by GPC method and 10-40g/10 minutes melt flow rate MFR and (B) 10-25 pts.wt. styrene ethylene/butylene styrene block copolymer and (C) 5-20 pts.wt. inorganic filler.

COPYRIGHT: (C)1994,JPO&Japio

$M_w/M_n$

$M_z/M_w$

mmmm

MFR

**BEST AVAILABLE COPY**